



Via Oberdan, 7 – 20059 Vimercate (MI)
Tel. : +39 039 6612297
Fax : +39 039 6612297
E-mail: info@fiortech.com
P.I.: 02916370139

TECHNICAL DATA SHEET

RT355 Fast Setting Flexible Epoxy System

Description

RT355 is a fast cure, thixotropic epoxy resin system with good adhesion to flexible substrates.

Benefits

- Sets in minutes at room temperature
- Will bond metals, glass, wood, rubbers and many plastics
- Good shock resistance
- Good temperature and oil resistance
- Supplied in DuoSyringe for easy application
- Standard size is 50ml, with associated mixing nozzles and dispenser guns
- Suitable for applications of less than 25 grams

Typical Properties

Curing (*measurements 10grams at 23°C*)

Work life: 5 – 10 minutes
Time to handling: 20 minutes
Time to full cure: 2 hours

Typical Performance (*measurements at 23 °C*)

Peel (Neoprene/Neoprene) 50N/25mm
Hardness (Shore A) 80
Operating temperature -40°C to +150°C

Colour

Black

Related Products

- RT112 non-sag, fast setting epoxy sealant
- RT125 flexible, high performance epoxy adhesive
- RT183 electrically conductive epoxy adhesive
- TriPatch wraparound epoxy repair system

September 2002

Issue 1

Fiortech warrants only that its products meet the specifications stated herein. Typical properties where stated are to be considered as representative of the current production and should not be treated as specifications. While the information presented is believed to be true and reliable, users are advised to conduct sufficient investigations to ensure the suitability of any product for its intended use. Fiortech cannot accept any responsibility for loss or damage that may result from the use of this information.

Web site: www.fiortech.com